

\*\*\*\*\*  
USACE / NAVFAC / AFCEC UFGS-07 61 14 (August 2025)

Preparing Activity: NAVFAC

-----  
Superseding  
UFGS-07 61 14.00 20 (August 2016)

## UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated October 2025

\*\*\*\*\*

### SECTION TABLE OF CONTENTS

#### DIVISION 07 - THERMAL AND MOISTURE PROTECTION

#### SECTION 07 61 14

#### STEEL STANDING SEAM ROOFING

08/25

#### PART 1 GENERAL

- 1.1 REFERENCES
- 1.2 DEFINITIONS
  - 1.2.1 Field-Formed Seam
  - 1.2.2 Snap Together Seam
  - 1.2.3 Pre-Formed
  - 1.2.4 Field-Formed
  - 1.2.5 Roofing System
  - 1.2.6 SSMRS
- 1.3 SYSTEM DESCRIPTION
  - 1.3.1 Design Requirements
  - 1.3.2 Design Conditions
    - 1.3.2.1 Wind Uplift
    - 1.3.2.2 Roof Live Loads
    - 1.3.2.3 Thermal Movement
    - 1.3.2.4 Deflection
  - 1.3.3 Structural Performance
- 1.4 SUBMITTALS
- 1.5 DESIGN CALCULATIONS
- 1.6 QUALITY CONTROL
  - 1.6.1 Preroofing Conference
  - 1.6.2 Manufacturer
  - 1.6.3 Manufacturer's Technical Representative
  - 1.6.4 Installer's Qualifications
  - 1.6.5 Single Source
  - 1.6.6 Laboratory Tests For Panel Finish
  - 1.6.7 Shop Drawings
  - 1.6.8 Dissimilar Metals
- 1.7 WARRANTY
  - 1.7.1 Metal Roof Panel Manufacturer Warranty
  - 1.7.2 Manufacturer's Finish Warranty
  - 1.7.3 Contractor Warranty
- 1.8 DELIVERY, STORAGE AND HANDLING

- 1.8.1 Delivery
- 1.8.2 Storage
- 1.8.3 Handling

## PART 2 PRODUCTS

- 2.1 ROOFING PANELS
  - 2.1.1 Material
  - 2.1.2 Texture
  - 2.1.3 Solar Reflectance
  - 2.1.4 Finish
    - 2.1.4.1 Factory Color Finish
- 2.2 INTERMEDIATE SUPPORTS
- 2.3 ATTACHMENT CLIPS
- 2.4 ACCESSORIES
  - 2.4.1 Closures
    - 2.4.1.1 Rib Closures
    - 2.4.1.2 Ridge Closures
  - 2.4.2 Fasteners
    - 2.4.2.1 Screws
    - 2.4.2.2 Bolts
    - 2.4.2.3 Automatic End-Welded Studs
    - 2.4.2.4 Explosive Driven Fasteners
    - 2.4.2.5 Rivets
  - 2.4.3 Sealants
  - 2.4.4 GASKETS AND INSULATING COMPOUNDS
- 2.5 THERMAL INSULATION
- 2.6 LINER PANELS

## PART 3 EXECUTION

- 3.1 EXAMINATION
- 3.2 PROTECTION FROM CONTACT WITH DISSIMILAR MATERIALS
  - 3.2.1 Cementitious Materials
  - 3.2.2 Contact with Wood
  - 3.2.3 Dissimilar Metals
- 3.3 INSTALLATION
  - 3.3.1 Roof Panels
  - 3.3.2 Insulation Installation
    - 3.3.2.1 Rigid or Semi-Rigid Insulation
    - 3.3.2.2 Blanket Insulation
  - 3.3.3 Flashings
  - 3.3.4 Flashing Fasteners
  - 3.3.5 Rib and Ridge Closure/Closure Strips
- 3.4 PROTECTION OF APPLIED ROOFING
- 3.5 CORRECTION OF DEFICIENCIES
- 3.6 CLEANING
- 3.7 MANUFACTURER'S FIELD INSPECTION
  - 3.7.1 Frequency
  - 3.7.2 Field Inspection Report
- 3.8 COMPLETED WORK
- 3.9 INFORMATION CARD
- 3.10 SCHEDULE
- 3.11 FORM ONE

-- End of Section Table of Contents --

\*\*\*\*\*  
USACE / NAVFAC / AFCEC UFGS-07 61 14 (August 2025)

Preparing Activity: NAVFAC

-----  
Superseding  
UFGS-07 61 14.00 20 (August 2016)

## UNIFIED FACILITIES GUIDE SPECIFICATIONS

References are in agreement with UMRL dated October 2025

\*\*\*\*\*

### SECTION 07 61 14

#### STEEL STANDING SEAM ROOFING 08/25

\*\*\*\*\*

NOTE: This guide specification covers the requirements for steel standing seam roofing.

Adhere to UFC 1-300-02 Unified Facilities Guide Specifications (UFGS) Format Standard when editing this guide specification or preparing new project specification sections. Edit this guide specification for project specific requirements by adding, deleting, or revising text. For bracketed items, choose applicable item(s) or insert appropriate information.

Remove information and requirements not required in respective project, whether or not brackets are present.

Comments, suggestions and recommended changes for this guide specification are welcome and should be submitted as a Criteria Change Request (CCR).

\*\*\*\*\*

\*\*\*\*\*

NOTE: This guide specification is primarily for Steel Structural Standing Seam Metal Roofing Systems (SSMRS), such as Self-Supporting Systems designed to span from purlin to purlin at slopes as low as **2 in 24** **1 inch per foot** versus architectural (non-structural) cladding systems that require continuous support, secondary moisture protection and slopes no less than **1 in 4** **3 inches per foot**. Structural systems may be used for architectural applications whereas architectural (non-structural) systems cannot be used for structural applications. If an SSMRS system is desired for architectural (non-structural) purposes, use Section **07 41 13** METAL ROOF PANELS; otherwise use this section. For aluminum structural standing seam metal roofing systems use Section **07 61 15** ALUMINUM STANDING SEAM ROOFING.

\*\*\*\*\*

\*\*\*\*\*

NOTE: Design exterior envelope to meet the requirements of UFC 1-200-02, "High Performance and Sustainable Building Requirements" which invokes the requirements within UFC 3-101-01, "Architecture". UFC 1-200-02 and UFC 3-101-01 make references throughout to various ASHRAE documents governing energy efficiency and requirements for the components of building envelope design including moisture control and thermal performance.

\*\*\*\*\*

\*\*\*\*\*

NOTE: On the drawings, show:

1. Roof slope
2. Supporting structural framework.
3. Intermediate support and attachment details, when applicable.
4. Attachment clip spacing.
5. Flashing support and fastening spacing.
6. Roof venting. (Pay particular attention to preventing infiltration of wind-driven rain.)
7. Sealant and closure locations.
8. Locations for dissimilar metal protection.
9. Details of accessories such as ladders, walkways, antenna mounts, guy wire fastening, ventilation equipment, snow restraints, and lightning rods.
10. Details of flashing at all roof penetrations. On roof plan add note to offset penetrations so center of penetrations coincide with mid-point of panel seams.
11. Design loads including stress diagram.
12. Location and attachment of permanent fall protection devices.

\*\*\*\*\*

\*\*\*\*\*

NOTE: When designing standing seam roofs, consider:

1. Consult with manufacturers early in design stage to obtain current manuals, specific guidance, and structural information regarding roof attachment. Early contact will reduce need for corrections and changes during review process and construction

phase. Ensure that system detailed and specified can be provided by three separate manufacturers.

2. Calculate wind uplift forces in accordance with UFC 3-110-03, "Roofing" and UFC 3-301-01, "Structural Engineering".. Submit calculations and stress diagram with design review package.

3. Minimum guidelines are 2 in 24 1 inch per foot for roof slopes. Provide greater slope if possible. In renovation of existing buildings, adequate slope must often be obtained by imaginative solutions. Prefabricated steel systems, sleepers, and stub walls have been used successfully, but attachment and structural stability of these must be assured. In some existing structures it will be difficult to design strong connections to structural system unless modifications are made to resist wind forces adequately.

4. Flashing presents a particular design problem in preventing wind and water infiltration. High winds and thermal movement create stresses in flashing which must be resisted by careful detailing of attachments.

While standing seam roofing presents continuous, sealed surface to the elements, flashing transitions are often the cause of serious problems. Overhangs are especially susceptible to high wind forces, and attachment at the edges should be carefully designed. Copious use of sealants and closure pieces molded to conform to the roof panels is imperative.

5. Building may require equipment such as antennae, ladders or lightning rods installed on roof. Access to roof-mounted mechanical equipment is often required. Provide walking surfaces and attachment accessories which do not compromise integrity of roof system. Design these accessories to provide support without penetrating roofing panels. Usually this is done with clamps attached to standing seam, or specially designed clips. Provide curbs or structural supports for mechanical equipment. Where condensate or other piping will be attached to or come in contact with roofing panels, ensure that the piping and anchorage materials are compatible with roof panel base metal to avoid corrosion from galvanic action. Ensure that condensate or other discharge of liquid onto roof panels will not stain or corrode panel finish or base metal.

\*\*\*\*\*

## PART 1 GENERAL

### 1.1 REFERENCES

\*\*\*\*\*

NOTE: This paragraph is used to list the publications cited in the text of the guide specification. The publications are referred to in the text by basic designation only and listed in this paragraph by organization, designation, date, and title.

Use the Reference Wizard's Check Reference feature when you add a Reference Identifier (RID) outside of the Section's Reference Article to automatically place the reference in the Reference Article. Also use the Reference Wizard's Check Reference feature to update the issue dates.

References not used in the text will automatically be deleted from this section of the project specification when you choose to reconcile references in the publish print process.

\*\*\*\*\*

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

AMERICAN ARCHITECTURAL MANUFACTURERS ASSOCIATION (AAMA)

AAMA 2605 (2022) Voluntary Specification, Performance Requirements and Test Procedures for Superior Performing Organic Coatings on Aluminum Extrusions and Panels

AMERICAN IRON AND STEEL INSTITUTE (AISI)

AISI D100 (2017) Cold-Formed Steel Design Manual

AMERICAN SOCIETY OF CIVIL ENGINEERS (ASCE)

ASCE 7-22 (2022; Supp 1 2023; Supp 2 2023; Supp 3 2025) Minimum Design Loads and Associated Criteria for Buildings and Other Structures

ASTM INTERNATIONAL (ASTM)

ASTM A36/A36M (2019) Standard Specification for Carbon Structural Steel

ASTM A653/A653M (2025) Standard Specification for Steel Sheet, Zinc-Coated (Galvanized) or Zinc-Iron Alloy-Coated (Galvannealed) by the Hot-Dip Process

ASTM A792/A792M (2025) Standard Specification for Steel Sheet, 55% Aluminum-Zinc Alloy-Coated by the Hot-Dip Process

ASTM A1008/A1008M (2024) Standard Specification for Steel, Sheet, Cold-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability,

Solution Hardened, and Bake Hardenable

ASTM A1011/A1011M	(2023) Standard Specification for Steel Sheet and Strip, Hot-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, and Ultra-High Strength
ASTM B117	(2019) Standard Practice for Operating Salt Spray (Fog) Apparatus
ASTM D522/D522M	(2017; R 2021) Mandrel Bend Test of Attached Organic Coatings
ASTM D523	(2014; R 2018) Standard Test Method for Specular Gloss
ASTM D714	(2002; R 2017) Standard Test Method for Evaluating Degree of Blistering of Paints
ASTM D968	(2022) Standard Test Methods for Abrasion Resistance of Organic Coatings by Falling Abrasive
ASTM D1654	(2008; R 2016; E 2017) Standard Test Method for Evaluation of Painted or Coated Specimens Subjected to Corrosive Environments
ASTM D2244	(2025) Standard Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates
ASTM D2247	(2025) Standard Practice for Testing Water Resistance of Coatings in 100 Percent Relative Humidity
ASTM D4214	(2023) Standard Test Method for Evaluating the Degree of Chalking of Exterior Paint Films
ASTM E84	(2024) Standard Test Method for Surface Burning Characteristics of Building Materials
ASTM E1592	(2025) Standard Test Method for Structural Performance of Sheet Metal Roof and Siding Systems by Uniform Static Air Pressure Difference
ASTM E1980	(2024) Standard Practice for Calculating Solar Reflectance Index of Horizontal and Low-Sloped Opaque Surfaces

COOL ROOF RATING COUNCIL (CRRC)

ANSI/CRRC S100	(2021) Standard Test Methods for Determining Radiative Properties of
----------------	----------------------------------------------------------------------

## Materials

FM GLOBAL (FM)

FM 4471

(2025) Class I Panel Roofs

NATIONAL ROOFING CONTRACTORS ASSOCIATION (NRCA)

NRCA CONDET

(2025) Construction Details Manual

SHEET METAL AND AIR CONDITIONING CONTRACTORS' NATIONAL ASSOCIATION  
(SMACNA)

SMACNA 1793

(2012) Architectural Sheet Metal Manual,  
7th Edition

UL SOLUTIONS (UL)

UL 580

(2006; Reprint Apr 2024) UL Standard for  
Safety Tests for Uplift Resistance of Roof  
Assemblies

### 1.2 DEFINITIONS

#### 1.2.1 Field-Formed Seam

Seams of panels so configured that when adjacent sheets are installed the seam is sealed utilizing mechanical or hand seamers. Crimped (45 degree bend), roll formed (180 degree bend), double roll formed (2 - 180 degree bends), and roll and lock systems are types of field-formed seam systems.

#### 1.2.2 Snap Together Seam

Panels so configured that the male and female portions of the seam interlock through the application of foot pressure or tamping with a mallet. Snap-on cap configurations are a type of snap together system.

#### 1.2.3 Pre-Formed

Formed to the final, less field-formed seam, profile and configuration in the factory.

#### 1.2.4 Field-Formed

Formed to the final, less field-formed seam, profile and configuration at the site of work prior to installation.

#### 1.2.5 Roofing System

The roofing system is defined as the assembly of roofing components, including roofing panels, flashing, fasteners, and accessories which, when assembled properly result in a watertight installation.

#### 1.2.6 SSMRS

Standing Seam Metal Roof System (SSMRS) is abbreviation of the entire roof system specified herein with all components and parts coming from a single manufacturer's system.



### 1.3 SYSTEM DESCRIPTION

#### 1.3.1 Design Requirements

- a. Provide panels in continuous lengths up to manufacturer's standard longest lengths, with no joints or seams, except where indicated or specified. Ribs of adjoining sheets must be in continuous contact from eave to ridge. Individual panels of snap together type systems must be removable for replacement of damaged material.
- b. There must be no exposed or penetrating fasteners except where shown on approved shop drawings. Provide a minimum of two fasteners per clip. Single fasteners will be allowed when supporting structural members are prepunched or predrilled.
- c. Snap together type systems must have a capillary break and a positive side lap locking device. Field-formed seam type systems must be mechanically locked closed by the manufacturer's locking tool. The seam must include a continuous factory applied sealant, or field applied sealant, or sealant tape when required by the manufacturer to withstand the wind loads specified.
- d. Provide concealed roof panel anchor clips designed to allow for longitudinal thermal movement of the panels, except where specific fixed points are indicated. Provide for lateral thermal movement in panel configuration or with clips designed for lateral and longitudinal movement.

#### 1.3.2 Design Conditions

Design the system to resist positive and negative loads specified herein in accordance with [AISI D100](#). Panels must support walking loads without permanent distortion or telegraphing of the structural supports.

##### 1.3.2.1 Wind Uplift

Provide metal roof panel system that conforms to the requirements of [ASTM E1592](#) and [UL 580](#). Uplift force due to wind action governs the design for panels. Submit [wind uplift test report](#) prior to commencing installation.

Provide roof system and attachments that resist the wind loads as determined by [ASCE 7-22](#), in pounds per square foot. Metal roof panels and component materials are to comply with the requirements in [FM 4471](#) as part of a panel roofing system as listed in Factory Mutual Guide (FMG) "Approval Guide" for class 1 or noncombustible construction, as applicable. Identify all materials with FMG markings.

##### 1.3.2.2 Roof Live Loads

\*\*\*\*\*  
**NOTE: Refer to UFC 3-301-01, "Structural Engineering" for additional requirements.**  
\*\*\*\*\*

Loads must be applied on the horizontal projection of the roof structure. The minimum roof design live load must be [1 kPa](#) [20 psf](#).

#### 1.3.2.3 Thermal Movement

\*\*\*\*\*  
NOTE: Insert design low temperature for the project location as obtained from UFC 3-400-02, "Design: Engineering Weather Data." Select first bracketed option for unpainted finish and light colors, select second bracketed option for dark colors.  
\*\*\*\*\*

System must be capable of withstanding thermal movement based on a temperature range of 5 degrees C 10 degrees F below [\_\_\_\_\_] degrees C F and [60 degrees C.][80 degrees C.] [140 degrees F.][180 degrees F.]

#### 1.3.2.4 Deflection

Panels must be capable of supporting design loads between unsupported spans with deflection of not greater than L/180 of the span.

#### 1.3.3 Structural Performance

\*\*\*\*\*  
NOTE: Full scale testing is required to certify the adequacy of the SSMRS. Once a SSMRS is certified for a specific loading condition, that certification may be used for future projects.  
\*\*\*\*\*

The structural performance test methods and requirements of the Standing Seam Roofing Systems (SSRS) must be in accordance with ASTM E1592.

#### 1.4 SUBMITTALS

\*\*\*\*\*  
NOTE: Review Submittal Description (SD) definitions in Section 01 33 00 SUBMITTAL PROCEDURES and edit the following list, and corresponding submittal items in the text, to reflect only the submittals required for the project. The Guide Specification technical editors have classified those items that require Government approval, due to their complexity or criticality, with a "G." Generally, other submittal items can be reviewed by the Contractor's Quality Control System. Only add a "G" to an item if the submittal is sufficiently important or complex in context of the project.

For Army projects, fill in the empty brackets following the "G" classification, with a code of up to three characters to indicate the approving authority. Codes for Army projects using the Resident Management System (RMS) are: "AE" for Architect-Engineer; "DO" for District Office (Engineering Division or other organization in the District Office); "AO" for Area Office; "RO" for Resident Office; and "PO" for Project Office. Codes following the "G" typically are not used for Navy and Air Force projects.

The "S" classification indicates submittals required as proof of compliance for sustainability Guiding Principles Validation or Third Party Certification and as described in Section 01 33 00 SUBMITTAL PROCEDURES.

\*\*\*\*\*

Government approval is required for submittals with a "G" or "S" classification. Submittals not having a "G" or "S" classification are for Contractor Quality Control approval. Submittals not having a "G" or "S" classification are for information only. When used, a code following the "G" classification identifies the office that will review the submittal for the Government. Submit the following in accordance with Section 01 33 00 SUBMITTAL PROCEDURES:

#### SD-02 Shop Drawings

Shop Drawings; G, [\_\_\_\_\_]

#### SD-03 Product Data

Roofing Panels; G, [\_\_\_\_\_]

Recycled Content for Steel Roofing Product; S

[ Heat Island Reduction; S

] Attachment Clips

Closures

Accessories

Fasteners

Sealants

[ Insulation

] Sample Warranty Certificate; G, [\_\_\_\_\_]

#### SD-04 Samples

Roofing Panel

[ Color Finish

] Accessories

Sealants

Intermediate Support Section

#### SD-05 Design Data

Design Calculations

#### SD-06 Test Reports

Wind Uplift Test Report; G, [\_\_\_\_\_]

Field Inspection; G, [\_\_\_\_\_]

\*\*\*\*\*  
NOTE: This paragraph requires certified test reports for structural and finish tests. If there is reason to require a factory test report for other tests, modify this paragraph accordingly.  
\*\*\*\*\*

Structural Performance Tests

Finish Tests

SD-07 Certificates

Manufacturer's Technical Representative's Qualifications

Statement of Installer's Qualifications

Coil Stock Compatibility; G, [\_\_\_\_\_]

SD-08 Manufacturer's Instructions

Installation Manual; G, [\_\_\_\_\_]

SD-11 Closeout Submittals

Information Card

Warranty

#### 1.5 DESIGN CALCULATIONS

\*\*\*\*\*  
NOTE: Ensure that appropriate design loads are specified in paragraph WIND UPLIFT.  
\*\*\*\*\*

Provide design calculations prepared by a professional engineer specializing in structural engineering verifying that system and additional framing meets design load criteria indicated. Coordinate calculations with manufacturer's test results. Include calculations for:

- a. Wind load uplift design pressure at roof locations specified in paragraph WIND UPLIFT.
- b. Clip spacing and allowable load per clip.
- c. Fastening of clips to structure or intermediate supports.
- d. Intermediate support spacing and framing and fastening to structure when required.
- e. Allowable panel span at anchorage spacing indicated.
- f. Safety factor used in design loading.

- g. Governing code requirements or criteria.
- h. Edge and termination details.

## 1.6 QUALITY CONTROL

### 1.6.1 Preroofing Conference

After submittals are received and approved but before roofing[ and insulation] work, including associated work, is performed, the Contractor must hold a preroofing conference to review the following:

- a. The drawings and specifications
- b. Procedure for on-site inspection and acceptance of the roofing substrate and pertinent structural details relating to the roofing system
- c. Contractor's plan for coordination of the work of the various trades involved in providing the roofing system and other components secured to the roofing
- d. Safety requirements

The preroofing conference must be attended by the Contractor and personnel directly responsible for the roofing[ and insulation] installation,[ [mechanical][ and][ electrical] work], and the roofing manufacturer's technical representative. Conflicts among those attending the preroofing conference must be resolved and confirmed in writing before roofing work, including associated work, is begun.[ Prepare written minutes of the preroofing conference and submit to the Contracting Officer.]

### 1.6.2 Manufacturer

The SSMRS must be the product of a metal roofing industry - recognized manufacturer who has been in the practice of manufacturing SSMRS for a period of not less than 5 years and who has been involved in at least 5 projects similar in size and complexity to this project.

### 1.6.3 Manufacturer's Technical Representative

The representative must have authorization from manufacturer to approve field changes and be thoroughly familiar with the products and with installations in the geographical area where construction will take place. The manufacturer's representative must be an employee of the manufacturer with at least 5 years experience in installing the roof system. The representative must be available to perform field inspections and attend meetings as required herein, and as requested by the Contracting Officer. Submit documentation from roofing manufacturer proving the manufacturer's technical representative meets specified requirements. Include name, address, telephone number, and experience record.

### 1.6.4 Installer's Qualifications

\*\*\*\*\*  
**NOTE: Specify 3 years as an approved Contractor  
unless directed otherwise by the Government.**  
\*\*\*\*\*

The roofing system installer must be approved, authorized, or licensed in writing by the steel roofing system manufacturer to install the system, and have a minimum of [3][\_\_\_\_\_] years experience as an approved applicator with that manufacturer, approved at a level capable of providing the specified warranty. The applicator must have applied five installations from the manufacturer being submitted of similar size, scope, and the same system as this project within the previous 3 years. Submit the names, locations, and client contact information of five projects of similar size and scope constructed by applicator using the manufacturer's roofing products submitted for this project within the previous 3 years.

#### 1.6.5 Single Source

Roofing panels, clips, closures, and other accessories must be standard products of the same manufacturer; must be the latest design by the manufacturer; and must have been designed by the manufacturer to operate as a complete system for the intended use.

#### 1.6.6 Laboratory Tests For Panel Finish

The term "appearance of base metal" refers to the metal coating on steel. Provide panels meeting the following test requirements:

- a. Formability Test: When subjected to a 180 degree bend over a 3 mm 1/8 inch diameter mandrel in accordance with ASTM D522/D522M, exterior coating film may show only slight microchecking and no loss of adhesion.
- b. Accelerated Weathering Test: Withstand a weathering test for a minimum of 2000 hours in accordance with AAMA 2605 without cracking, peeling, blistering, loss of adhesion of the protective coating, or corrosion of the base metal. Protective coating that can be readily removed from the base metal with a penknife blade or similar instrument will be considered to indicate loss of adhesion.
- c. Chalking Resistance: After the 2000-hour weatherometer test, exterior coating may not chalk greater than No. 8 rating when measured in accordance with ASTM D4214 test procedures.
- d. Color Change Test:

\*\*\*\*\*  
NOTE: In general, only neutral colors such as white, beige, and tan will not exceed the 2 NBS units requirement. To allow for bold, heavier pigmented colors, specify color change not to exceed 5 NBS units for a 3000-hour weatherometer test.  
\*\*\*\*\*

- e. After the [2000][\_\_\_\_\_] -hour weatherometer test, exterior coating color change must not exceed [2][5] [\_\_\_\_\_] NBS units when measured in accordance with ASTM D2244 test procedure.

\*\*\*\*\*  
NOTE: For projects located in humid locations or project locations with Environmental Severity Classifications (ESC) of C3 thru C5 or where premium

finish would be justified, use:

Salt spray test: Rating of 10, no blisters in field  
Rating of 7, 2 mm 1/16 inch edge creep

Abrasion Resistance Test: 100 liters

Humid locations are those in ASHRAE climate zones  
0A, 1A, 2A, 3A, 3C, 4C and 5C (as identified in  
ASHRAE 90.1). See UFC 1-200-01 for determination of  
ESC for project locations.

\*\*\*\*\*

- f. Salt Spray Test: Withstand a salt spray test for a minimum of 1000 hours in accordance with ASTM B117, including the scribe requirement in the test. Immediately upon removal of the panel from the test, the coating must receive a rating of [ 8, few blisters][ 10, no blisters] in field as determined by ASTM D714; and an average rating of [6, 3 mm][7, 2 mm] [6, 1/8 inch][7, 1/16 inch] failure at scribe, as determined by ASTM D1654. Rating Schedule No. 1.
- g. Abrasion Resistance Test for Color Coating: When subjected to the falling sand test in accordance with ASTM D968, coating system must withstand a minimum of [50][100][\_\_\_\_\_] liters of sand per mil thickness before appearance of base metal.
- h. Humidity Test: When subjected to a humidity cabinet test in accordance with ASTM D2247 for 1000 hours, a scored panel must show no signs of blistering, cracking, creepage, or corrosion.
- i. Gloss Test: The gloss of the finish must be 30 plus or minus 5 at an angle of 60 degrees, when measured in accordance with ASTM D523.
- [ j. Glare Resistance Test:

\*\*\*\*\*

NOTE: Include the requirements for glare resistance only when specifically required by the facility for critical glare areas such as control towers or other structures where glare can be an operational hazard. Refer to UFC 4-211-01, "Aircraft Maintenance Hangars" for assistance in determining critical glare areas. Delete gloss test above if this paragraph is included.

\*\*\*\*\*

- k. Surfaces of panels that will be exposed to the exterior must have a specular reflectance of not more than 10 when measured in accordance with ASTM D523 at an angle of 85 degrees. Specular reflectance may be obtained with striations or embossing. Requirements specified under FORMABILITY TEST will be waived if necessary to conform to this requirement.

#### 11.6.7 Shop Drawings

Submit roofing drawings to supplement the instructions and diagrams. Include design and erection drawings containing an isometric view of the roof showing the design uplift pressures and dimensions of edge, ridge and corner zones; and show typical and special conditions including flashings,

materials and thickness, dimensions, fixing lines, anchoring methods, sealant locations, sealant tape locations, fastener layout, sizes, and spacing, terminations, penetrations, attachments, and provisions for thermal movement. Details of installation must be in accordance with the manufacturer's Standard Instructions and details or the [NRCA CONDET](#) or [SMACNA 1793](#). Prior to submitting shop drawings, have drawings reviewed and approved by the manufacturer's technical engineering department.

#### 1.6.8 Dissimilar Metals

Ensure that no dissimilar metals that may cause corrosion by galvanic action in certain exposures are in direct contact with one another in any part of the roof assembly.

#### 1.7 [WARRANTY](#)

\*\*\*\*\*  
**NOTE: This warranty paragraph may be used with this  
guide specification without special authorization.**  
\*\*\*\*\*

Provide metal roof system material and workmanship warranties meeting specified requirements. Provide revision or amendment to manufacturer's standard warranty as required to comply with the specified requirements. Submit a [sample warranty](#) certificate during the pre-construction phase to prove all warranty requirements will be achieved.

##### 1.7.1 Metal Roof Panel Manufacturer Warranty

\*\*\*\*\*  
**NOTE: Select the appropriate warranty duration.  
Specify a minimum 20-year warranty unless directed  
otherwise by the Government.**  
\*\*\*\*\*

Furnish the metal roof panel manufacturer's [20][30]-year no dollar limit roof system materials and installation workmanship warranty, including flashing,[ insulation,] components, trim, and accessories necessary for a watertight roof system construction. Write warranty directly to the Government, commencing at time of Government's acceptance of the roof work. The warranty is required to state that:

- a. If within the warranty period, the metal roof system, as installed for its intended use in the normal climatic and environmental conditions of the facility, becomes non-watertight, shows evidence of moisture intrusion within the assembly, displaces, corrodes, perforates, separates at the seams, or shows evidence of excessive weathering due to defective materials or installation workmanship, the repair or replacement of the defective and damaged materials of the metal roof system and correction of defective workmanship is the responsibility of the metal roof panel manufacturer. All costs associated with the repair or replacement work are the responsibility of the metal roof panel manufacturer.
- b. If the manufacturer or his approved applicator fail to perform the repairs within 72 hours of notification, emergency temporary repairs performed by others does not void the warranty.



### [1.7.2 Manufacturer's Finish Warranty

\*\*\*\*\*  
**NOTE: Include the following paragraph when factory  
color finish panels are specified.**  
\*\*\*\*\*

Provide a manufacturer's no-dollar-limit 20-year warranty for the roofing system. Issue the warranty directly to the Government at the date of Government acceptance, warranting that the factory color finish, under normal atmospheric conditions at the site, will not crack, peel, or delaminate; chalk in excess of a numerical rating of 8 when measured in accordance with [ASTM D4214](#); or fade or change colors in excess of 5 NBS units as measured in accordance with [ASTM D2244](#).

### ]1.7.3 Contractor Warranty

\*\*\*\*\*  
**NOTE: Select five5 years for Army and Air Force  
projects and 2 years for all other projects.**  
\*\*\*\*\*

Provide Contractor's No Dollar Limit warranty for a period of not less than [2][5] years that the roof system, as installed, is free from defects in installation workmanship, to include the roof panel installation, flashing,[ insulation,] accessories, attachments, and sheet metal installation integral to a complete watertight roof system assembly. Issue warranty directly to the Government. Correction of defective workmanship and replacement of damaged or affected materials is the responsibility of the Contractor. All costs associated with the repair or replacement work are the responsibility of the Contractor.

## 1.8 DELIVERY, STORAGE AND HANDLING

Deliver, store, and handle preformed panels, bulk roofing products and other manufactured items in a manner to prevent damage or deformation.

### 1.8.1 Delivery

Provide adequate packaging to protect materials during shipment. Crated materials must not be uncrated until ready for use, except for inspection. Immediately upon arrival of materials at the jobsite, inspect materials for damage, dampness, and staining. Replace damaged or permanently stained materials that cannot be restored to like-new condition with satisfactory material. If materials are wet, remove the moisture and re-stack and protect the panels until used.

### 1.8.2 Storage

Stack materials on platforms or pallets and cover with tarpaulins or other suitable weathertight covering which prevents water trapping or condensation. Store materials so that water which might have accumulated during transit or storage will drain off. Do not store the panels in contact with materials that might cause staining, such as mud, lime, cement, fresh concrete or chemicals. Protect stored panels from wind damage.

### 1.8.3 Handling

Handle material carefully to avoid damage to surfaces, edges and ends.

## PART 2 PRODUCTS

### 2.1 ROOFING PANELS

\*\*\*\*\*

NOTE: Facilities with dominant cooling loads or in mild or warm climate zones are required to meet "cool roofing" requirements of FEMP. Cool roof design must follow the requirements in UFC 3-110-03, "Roofing", ASHRAE 90.1 Chapter 5, for the design of insulation and energy performance of the building. Design insulation for cool roofs to meet at a minimum the ASHRAE 90.1 Chapter 5 zone requirements.

NOTE: If the project includes a low-slope roof (less than 2:12) and a cool roof is selected, meet the ASHRAE 90.1 Chapter 5 values for roof insulation, roof Solar Reflectance Index (SRI), solar reflectance and thermal emittance. If a cool roof is not selected in ASHRAE zones 0 thru 3, design must meet one of the exception requirements listed in ASHRAE 90.1 Chapter 5 or provide thermal insulation as stated therein. Coordinate these requirements with insulation design and specifications.

\*\*\*\*\*

Provide panels with interlocking ribs for securing adjacent sheets and with concealed clip fastening system for securing the roof covering to structural framing members. Fasteners must not penetrate the panels except at the ridge, eave, rakes, penetrations, and end laps. Backing plates and ends of panels at end laps must be predrilled or prepunched. Factory prepare ends of panels to be lapped by trimming part of seam, die-setting, or swaging ends of panels. Individual sheets must be sufficiently long to cover the entire length of unbroken roof slope when such slope is 9 meters 30 feet or less. Provide panels that extend over two or more spans when length of run exceeds 18 meters 60 feet. Sheets must provide not less than 300 mm 12 inches of coverage (width) in place.[ Provide panels with a minimum corrugation height of [45][57][76] mm [1.75][2.25][3.0] inches (nominal).] Provide panels as indicated on drawings.] Make provisions for expansion and contraction at either ridge or eave, consistent with the type of system to be used. Form panels from coil stock without warping, waviness or ripples not part of the panel profile, and free of damage to the finish coating system. Provide certification of coil compatibility with roll forming machinery to be used for forming panels without warping, waviness, and rippling not part of panel profile; to be done without damage, abrasion or marking of finish coating. Submit a 300 mm 12 inch long by full width section of typical panel showing metal gage and seam.

#### 2.1.1 Material

\*\*\*\*\*

NOTE: Select Aluminum-zinc alloy coated steel (AZ 55) in humid locations or project locations with

Environmental Severity Classifications (ESC) of C3 thru C5. Zinc-coated steel with G90 coating is also an option for ESC locations of C1 or C2. Humid locations are those in ASHRAE climate zones 0A, 1A, 2A, 3A, 3C, 4C and 5C (as identified in ASHRAE 90.1). See UFC 1-200-01 for determination of ESC for project locations.

For minimum thickness of panel, UFC 3-110-03 allows minimum 0.6 mm 0.023 inch (24 gage) except where heavier gage is required to meet wind uplift criteria. However, a heavier section thickness of minimum 0.8 mm 0.030 inch (22 gage) may improve aesthetic with respect to oil canning.

Research shows the product is available from U.S. national manufacturers above the minimum recycled content stated. Some manufacturers and regions have higher percentages.

\*\*\*\*\*

[Aluminum-zinc alloy coated steel conforming to ASTM A792/A792M, AZ 165 AZ 55 coating; coating application rate must be minimum 15.6 g per 0.1 m<sup>2</sup> 0.55 oz. per ft.<sup>2</sup> for unpainted material (AZ55) and minimum 14.2 g per 0.1 m<sup>2</sup> 0.50 oz. per ft.<sup>2</sup> for pre-painted material (AZ50)][ or zinc-coated steel conforming to ASTM A653/A653M, Z275 G90 coating designation]. Provide material with a minimum, not including metallic coating thickness of 0.6 mm 0.023 inch thick (24 gage) minimum except when mid field of roof is subject to design wind uplift pressures of 3 kPa 60 psf or greater, entire roof system must have a minimum thickness of 0.8 mm 0.030 inch (22 gage). Steel roofing materials must contain a minimum of 30 percent total recycled content. Provide data identifying percentage of recycled content for steel roofing product.[ Prior to shipment, treat mill finish panels with a passivating chemical and oil to inhibit the formation of oxide corrosion products. Dry, retreat, and re-oil panels that have become wet during shipment or storage but have not started to oxidize.]

#### 2.1.2 Texture

\*\*\*\*\*

NOTE: Stucco embossing is a mechanical process that imparts some structural strength to the steel and reduces the visual effect of oil-canning. Embossed texture is slightly more expensive than smooth texture but should be considered for use on high visibility projects.

\*\*\*\*\*

[Stucco embossed.][ Smooth.][ Smooth with raised intermediate ribs for added stiffness.][ Smooth with striations across roof panel width.]

#### 2.1.3 Solar Reflectance

\*\*\*\*\*

NOTE: Retain the first bracketed sentence for low-slope roofing (less than 2:12) projects in ASHRAE climate zones 0 thru 3 with cool roof requirement. When a designer desires IgCC

compliance with cool roof requirements, include the second set of bracketed sentences for projects in ASHRAE climate zones 0 thru 3; see IgCC Chapter 5 for exceptions when design conditions eliminate these requirements. Retain the last bracketed sentence for project with sustainable third party certification credit requirement for reduced heat island effect.

\*\*\*\*\*

Provide roof finishes for more than 75 percent of the roof surface having a minimum 3-year aged solar reflectance of 0.55, and a minimum 3-year aged thermal emittance of 0.75 when tested in accordance with ANSI/CRRC S100, or, a minimum 3-year aged Solar Reflectance Index of 64 when determined in accordance with the Solar Reflectance Index method in ASTM E1980 using a convection coefficient of 6.62 W per m2 2.1 BTU per ft2.[ Use roofing materials having minimum 3-year aged SRI for more than 75 percent of roof surface (less than or equal to 2:12 slope, SRI greater than 64; greater than 2:12 slope, SRI greater than 25).] Provide emittance and reflectance percentages, solar reflectance index values,[ and] slopes [\_\_\_\_], to meet sustainable third party certification requirements for Heat Island Reduction.]

#### 2.1.4 Finish

\*\*\*\*\*

NOTE: Choose finish appropriate for the project. Per UFC 3-110-03, the preferred protective coating for carbon steel is 55 percent (by weight) aluminum-zinc alloy (such as Galvalume). When unpainted 55 percent AlZn (such as Galvalume) material is used it must have an additional protective coating of acrylic. In humid environments or project locations with an Environmental Severity Classification (ESC) of C3 thru C5, AZ55 Steel with PVDF coating should be selected. Galvanized steel (G90) with or without a coating is not acceptable unless the building is temporary. Humid locations are those in ASHRAE climate zones 0A, 1A, 2A, 3A, 3C, 4C and 5C (as identified in ASHRAE 90.1). See UFC 1-200-01 for determination of ESC for project locations. Delete paragraph LABORATORY TESTS FOR PANEL FINISH and reference to finishes when unpainted finish is specified. Some paint colors are substantially more costly than others, due to scarcity of pigments.

\*\*\*\*\*

[Unpainted][Factory color finish].

##### [2.1.4.1 Factory Color Finish

\*\*\*\*\*

NOTE: Provide clear edge coating on metal panels for project locations with Environmental Severity Classifications (ESC) of C3 thru C5. Humid locations are those in ASHRAE climate zones 0A, 1A, 2A, 3A, 3C, 4C and 5C (as identified in ASHRAE

90.1). See UFC 1-200-01 for determination of ESC for project locations.

\*\*\*\*\*

\*\*\*\*\*

NOTE: Check with the facility regarding color selection. Use only manufacturer's standard colors. Delete this subparagraph if unpainted finish has been selected. Coating thicknesses and materials are for panels in exterior applications; if panels will be used in interior conditioned spaces, edit information as appropriate.

Choose coating system appropriate for the project and location. Bracketed options are provided to allow for manufacturer variety. Manufacturer options may include a thicker primer, an additional barrier coat, or clear coat for enhanced protection.

For projects in humid locations and locations with Environmental Severity Classifications (ESC) of C3 thru C5 or local corrosive environment (Jet fuel) with Neutral color (white, tan or beige): Provide exterior finish coat of 70 percent resin polyvinylidene fluoride containing 100 percent inorganic pigments with no less than 0.040 mm 1.6 mil dry film thickness, consisting of 0.020 mm 0.8 mil prime coat and 0.020 mm 0.8 mil finish coat minimum applied by the continuous coil coating method. Interior/underside finish must consist of 0.010 mm 0.4 mil prime coat and 0.010 mm 0.4 mil backer coat dry film thickness).

For projects in humid locations and locations with Environmental Severity Classifications (ESC) of C3 thru C5 or local corrosive environment (Jet fuel) with Bold Vibrant color: Provide exterior finish coat of 70 percent resin polyvinylidene fluoride containing 100 percent inorganic pigments with no less than 0.060 mm 2.4 mil total dry film thickness, consisting of 0.020 mm 0.8 mil prime coat and 0.020 mm 0.8 mil finish coat and 0.020 mm 0.8 mil clear coat minimum applied by the continuous coil coating method. Interior/underside finish must consist of 0.010 mm 0.4 mil dry film thickness prime coat and 0.010 mm 0.4 mil dry film thickness backer coat).

For projects in locations with Environmental Severity Classifications (ESC) of C1 or C2, with Neutral color (white, tan or beige): Provide exterior finish coat of 70 percent resin polyvinylidene fluoride containing 100 percent inorganic pigments with not less than 0.025 mm 1.0 mil dry film thickness, consisting of 0.005 mm 0.2 mil prime coat and 0.020 mm 0.8 mil finish coat minimum applied by the continuous coil coating method. Interior/underside finish must consist of 0.005 mm 0.2 mil dry film thickness prime coat and 0.0075 mm 0.3 mil dry film thickness backer coat).

For projects in locations with Environmental Severity Classifications (ESC) of C1 or C2, with bold color: Provide exterior finish coat of 70 percent resin polyvinylidene fluoride containing 100 percent inorganic pigments with not less than 0.038 mm 1.5 mil dry film thickness, consisting of 0.005 mm 0.2 mil prime coat and 0.020 mm 0.8 mil finish coat and 0.013 mm 0.5 mil clear coat minimum applied by the continuous coil coating method. Interior/underside finish must consist of 0.005 mm 0.2 mil dry film thickness prime coat and 0.0075 mm 0.3 mil dry film thickness backer coat).

\*\*\*\*\*

Provide factory applied, thermally cured coating to exterior and interior of metal roof and wall panels and metal accessories. Provide exterior finish coat of [ 70 percent resin polyvinylidene fluoride containing 100 percent inorganic pigments] [\_\_\_\_\_] with not less than [0.025 mm][0.040 mm] [1.0 mil][ 1.6 mil] dry film thickness, consisting of [0.005 mm][0.020 mm] [0.2 mil][0.8 mil] prime coat and 0.020 mm 0.8 mil finish coat minimum applied by the continuous coil coating method. Interior/underside finish must consist of [ minimum [0.005 mm][0.010 mm] [0.2 mil][0.4 mil] dry film thickness prime coat and [0.0075 mm][0.010 mm] [0.3 mil][0.4 mil] dry film thickness backer coat][the same coating and dry film thickness as the exterior coating] [\_\_\_\_\_] .[ Apply a clear coating over finish coating to a dry film thickness of [0.0125 mm][0.020 mm] [0.5 mil][0.8 mil].][ For unpainted panels, provide an additional protective acrylic coating of minimum thickness 0.0075 mm 0.3 mil.] Provide exterior[ and interior] coating meeting test requirements specified below. Paint coatings must be applied over the corrosion treatments. Tests must have been performed on the same factory finish and thickness provided.[ Provide clear factory edge coating on all factory cut or unfinished edges.]

[ For color selection, submit 50 by 100 mm 2 by 4 inch metal samples in color, finish and texture[ specified][ selected].[ When colors are not indicated, submit samples of not less than six different manufacturer's standard colors for selection.]

## ]]2.2 INTERMEDIATE SUPPORTS

Fabricate panel subgirts, subpurlins, T-bars, Z-bars and tracks from galvanized steel conforming to ASTM A653/A653M, Z275 G90, Grade D (1.6 mm thick 16 gage and heavier), Grade A (1.3 mm thick 18 gage and lighter); or steel conforming to ASTM A36/A36M, ASTM A1011/A1011M, or ASTM A1008/A1008M prime painted with zinc-rich primer. Size, shape, thickness and capacity as required to meet the load[, insulation thickness] and deflection criteria specified. Submit full size samples of each intermediate support section, 300 mm 12 inches long.

## 2.3 ATTACHMENT CLIPS

Fabricate clips from ASTM A1011/A1011M, or ASTM A1008/A1008M steel hot-dip galvanized in accordance with ASTM A653/A653M, Z275 G 90, or Series 300 stainless steel. Size, shape, thickness and capacity as required to meet the load, insulation thickness and deflection criteria specified.

## 2.4 ACCESSORIES

Sheet metal flashings, [ gutters, ] [ downspouts, ] trim, moldings, closure strips, pre-formed crickets, caps, equipment curbs, and other similar sheet metal accessories used in conjunction with preformed metal panels must be of the same material as used for the panels. Provide metal accessories with a factory color finish to match the roofing panels, except that such items which will be concealed after installation may be provided without the finish if they are stainless steel. Metal must be of a thickness not less than that used for the panels. Thermal spacer blocks and other thermal barriers at concealed clip fasteners must be as recommended by the manufacturer except that wood spacer blocks are not allowed. Submit samples of each type of accessory item used in the project including, but not limited to each type of anchor clip, closure, fastener, and leg clamp.

### 2.4.1 Closures

#### 2.4.1.1 Rib Closures

Corrosion resisting steel, closed-cell or solid-cell synthetic rubber, neoprene or polyvinyl chloride pre-molded to match configuration of rib opening. Material for closures must not absorb water.

#### 2.4.1.2 Ridge Closures

Metal-clad foam or metal closure with foam secondary closure matching panel configuration for installation on surface of roof panel between panel ribs at ridge and headwall roof panel flashing conditions and terminations. Foam material must not absorb water.

### 2.4.2 Fasteners

\*\*\*\*\*

NOTE: Select first set of brackets for project locations with ESC C3 thru C5; select second set of brackets for project locations with ESC C1 or C2. See UFC 1-200-01 for determination of ESC for project locations.

"304 stainless cast head" or "304 stainless bi-metal" are preferred when the base metal (structural member or decking being attached to) consists of steel, cast iron, zinc, galvanized, galvalume or coated steel. These fasteners have a bimetallic construction and differ from "304 stainless steel" fasteners. "304 stainless steel" refers to fasteners which are fabricated entirely from 304 stainless steel. These may accelerate corrosion of certain base metals in some conditions. Consult with manufacturer for specific conditions where they are acceptable.

410 stainless steel fasteners may corrode base metal (structural member or decking being attached to) consisting of steel, cast iron, zinc, galvanized, galvalume or coated steel. Consult with manufacturer for specific conditions where they are accessible.

\*\*\*\*\*

[304 stainless steel, 304 stainless cast head or 304 stainless bi-metal ] [Zinc-coated steel, multi coated (zinc plus anti-corrosion coating, zinc cast head, or 410 stainless ] steel, type and size specified below or as otherwise approved for the applicable requirements. Electroplated zinc fasteners are not permitted for use. Design the fastening system to withstand the design loads specified. Exposed fasteners must be gasketed or have gasketed washers on the exterior side of the covering to waterproof the penetration. Washer material must be compatible with the covering; have a minimum diameter of 10 mm 3/8 inch for structural connections; and gasketed portion of fasteners or washers must be neoprene or other equally durable elastomeric material approximately 3 mm 1/8 inch thick.

#### 2.4.2.1 Screws

Not smaller than 4.75 mm No. 14 diameter if self-tapping type and not smaller than 4 mm No. 12 diameter if self-drilling and self-tapping.

#### 2.4.2.2 Bolts

Not smaller than 6 mm 1/4 inch diameter, shouldered or plain shank as required, with proper nuts.

#### 2.4.2.3 Automatic End-Welded Studs

Automatic end-welded studs must be shouldered type with a shank diameter of not smaller than 5 mm 3/16 inch and cap or nut for holding covering against the shoulder.

#### 2.4.2.4 Explosive Driven Fasteners

Fasteners for use with explosive actuated tools must have a shank diameter of not smaller than 4 mm 0.145 inch with a shank length of not smaller than 13 mm 1/2 inch for fastening to steel and not smaller than 25 mm 1 inch for fastening to concrete.

#### 2.4.2.5 Rivets

Blind rivets must be stainless steel with 3 mm 1/8 inch nominal diameter shank. Rivets must be threaded stem type if used for other than the fastening of trim. Rivets with hollow stems must have closed ends.

#### 2.4.3 Sealants

Elastomeric type containing no oil or asphalt. Exposed sealant must cure to a rubberlike consistency. Concealed sealant must be the non-hardening type. Seam sealant must be factory-applied, non-skinning, non-drying, and must conform to the roofing manufacturer's recommendations. Silicone-based sealants must not be used in contact with finished metal panels and components unless approved otherwise by the Contracting Officer.

#### 2.4.4 GASKETS AND INSULATING COMPOUNDS

Nonabsorptive and suitable for insulating contact points of incompatible materials. Insulating compounds must be nonrunning after drying.



## [2.5 THERMAL INSULATION

\*\*\*\*\*

NOTE: Include insulation in appropriate section; use this paragraph if a Division 07 Section is not included in project specifications. Insulation must meet minimum requirements in ASHRAE 90.1. Most manufacturers recommend batts with minimum thickness of 38 mm 1 1/2 inches for standing seam systems to minimize condensation on underside of roofing sheets and for sound attenuation. Spacer blocks should be required with insulation. 100 mm 4 inches (R 25) is the recommended maximum thickness; thicker insulation when compressed with thermal spacer/block affects lay of panel and setting of attachment clips over area of compressed insulation.

\*\*\*\*\*

Flexible blanket, rigid, or semi-rigid faced[ with a flexible vapor retarder]. Insulation and facing must have a flame-spread rating of 50 or less in accordance with ASTM E84.[ Vapor retarder facing must have a permeance rating of 0.05 perm or less.] Provide a thermal resistance "R" value of [\_\_\_\_\_] or more.[ Exposed insulation must have a white nondusting and nonshedding finish.] Facings[ and finishes] must be factory-applied.

## ]2.6 LINER PANELS

Fabricate liner panels of the same material as roof panels, and formed or patterned to prevent waviness and distortion. Liner panels must have a factory applied, one mil thick minimum painted coating on the inside face and a prime coat on the liner side.

## PART 3 EXECUTION

Do not install building construction materials that show visible evidence of biological growth.

### 3.1 EXAMINATION

Examine surfaces to receive standing seam metal roofing and flashing. Ensure that surfaces are plumb and true, clean, even, smooth, as dry and free from defects and projections which might affect the installation.

### 3.2 PROTECTION FROM CONTACT WITH DISSIMILAR MATERIALS

#### 3.2.1 Cementitious Materials

Paint metal surfaces which will be in contact with mortar, concrete, or other masonry materials with one coat of alkali-resistant coating such as heavy-bodied bituminous paint.

#### 3.2.2 Contact with Wood

Where metal will be in contact with wood or other absorbent material subject to wetting, seal joints with sealing compound and apply one coat of heavy-bodied bituminous paint.

### 3.2.3 Dissimilar Metals

When dissimilar metals may be in direct contact and result in corrosion by galvanic action, install a bond break or similar neutral material which serves to isolate the metals from contact.

## 3.3 INSTALLATION

Install in accordance with the approved manufacturer's erection instructions, shop drawings, and diagrams. Submit manufacturers printed installation manual, instructions, and standard details. Panels must be in full and firm contact with attachment clips. Where prefinished panels are cut in the field, or where the factory applied coverings or coatings are abraded or damaged in handling or installation, they must, after necessary repairs have been made with material of the same color as the weather coating, be approved by the Contracting Officer before being installed. Seal completely openings through panels. Correct defects or errors in the materials. Replace materials which cannot be corrected in an approved manner with nondefective materials. Provide molded closure strips where indicated and where necessary to provide weathertight construction. Use shims as required to ensure attachment clip line is true. Use a spacing gage at each row of panels to ensure that panel width is not stretched or shortened.

### 3.3.1 Roof Panels

Apply roofing panels with the standing seams parallel to the slope of the roof. Provide roofing panels in longest practical lengths from ridge to eaves (top to eaves on shed roofs), with no transverse joints except at the junction of ventilators, curbs, skylights, chimneys, and similar openings. Install flashing to assure positive water drainage away from roof penetrations. Locate panel end laps such that fasteners do not engage supports or otherwise restrain the longitudinal thermal movement of panels. Form field-formed seam type system seams in the field with an automatic mechanical seamer approved by the manufacturer. Attach panels to the structure with concealed clips incorporated into panel seams. Clip attachment must allow roof to move independently of the structure, except at fixed points as indicated.

### [3.3.2 Insulation Installation

\*\*\*\*\*  
**NOTE: For applications where permeability is a critical consideration, specify sealing of the insulation joints or other methods of providing continuity of the vapor retarder. Review overall roof construction to assure permeability is consistent with requirements specified for the vapor retarder.**  
\*\*\*\*\*

Install between covering and supporting members to present a neat appearance. Fold and staple and tape seams unless approved otherwise by the Contracting Officer.

### 3.3.2.1 Rigid or Semi-Rigid Insulation

Install in areas where insulation is exposed to view. Fasten securely without loose joints or unsightly sags.

### 3.3.2.2 Blanket Insulation

May be used in concealed locations. Lap facing at joints and fasten in a manner that will provide tight joints.

### 3.3.3 Flashings

\*\*\*\*\*  
NOTE: In high winds, metal will vibrate and fatigue at fasteners on "normal" spacings. For this reason, cleated (blind fastened) flashings are not acceptable, and attachment at 150 to 200 mm 6 to 8 inches on center is customary. Flashing should not extend more than one inch beyond a support or fastener.  
\*\*\*\*\*

Provide flashing, related closures and accessories as indicated and as necessary to provide a weathertight installation. Install flashing to ensure positive water drainage away from roof penetrations. Flash and seal the roof at the ridge, eaves and rakes, and projections through the roof. Place closure strips, flashing, and sealing material in an approved manner that will assure complete weathertightness. Details of installation which are not indicated must be in accordance with NRCA CONDET, SMACNA 1793, panel manufacturer's approved printed instructions and details, or the approved shop drawings. Allow for expansion and contraction of flashing.

### 3.3.4 Flashing Fasteners

Fastener spacings must be in accordance with the panel manufacturer's recommendations and as necessary to withstand the design loads indicated. Install fasteners in roof valleys as recommended by the manufacturer of the panels. Install fasteners in straight lines within a tolerance of 13 mm 1/2 inch in the length of a bay. Drive exposed penetrating type fasteners normal to the surface and to a uniform depth to seat gasketed washers properly and drive so as not to damage factory applied coating. Exercise extreme care in drilling pilot holes for fastenings to keep drills perpendicular and centered. Do not drill through sealant tape. After drilling, remove metal filings and burrs from holes prior to installing fasteners and washers. Torque used in applying fasteners must not exceed that recommended by the manufacturer. Remove panels deformed or otherwise damaged by over-torqued fastenings, and provide new panels.

### 3.3.5 Rib and Ridge Closure/Closure Strips

Set closure/closure strips in joint sealant material and apply sealant to mating surfaces prior to adding panel.

## 3.4 PROTECTION OF APPLIED ROOFING

Do not permit storing, walking, wheeling, or trucking directly on applied roofing materials. Provide temporary walkways, runways, and platforms of smooth clean boards or planks as necessary to avoid damage to applied roofing materials, and to distribute weight to conform to indicated live load limits of roof construction.

### 3.5 CORRECTION OF DEFICIENCIES

Where any form of deficiency is found, take additional measures as deemed necessary by the Contracting Officer to determine the extent of the deficiency and perform corrective actions as directed by the Contracting Officer.

### 3.6 CLEANING

Clean exposed sheet metal work at completion of installation. Remove metal shavings, filings, nails, bolts, and wires from roofs. Remove grease and oil films, excess sealants, handling marks, contamination from steel wool, fittings and drilling debris and scrub the work clean. Exposed metal surfaces must be free of dents, creases, waves, scratch marks, solder or weld marks and damage to the finish coating.

### [3.7 MANUFACTURER'S FIELD INSPECTION

\*\*\*\*\*

**NOTE:** Include this paragraph when manufacturer's inspection of work is required. Select desired frequency of manufacturer inspection and coordinate with bracketed options. Use bracketed option in second paragraph to specify minimum number of required visits. The minimum and default is three visits during installation. To help determine if more than three visits should be specified, divide the total project roof area in squares by 100 and round to the nearest whole number. Coordinate this requirement with Section 01 45 00 QUALITY CONTROL, paragraph QUALITY CONTROL (QC) SPECIALISTS - Experience Matrix.

\*\*\*\*\*

The roofing material manufacturer's technical representative must visit the work site to inspect ongoing work. Inspections are to include observing installation technique and verifying the quality of work-in-place for compliance with the manufacturer's instructions. Deficiencies identified by the manufacturer's technical representative must be corrected and re-inspected by the manufacturer's technical representative.

#### 3.7.1 Frequency

The manufacturer's technical representative must visit the work site to inspect and document ongoing work a minimum of [three][\_\_\_\_\_] separate occasions during the course of the installation. One visit must occur during the first 20 squares of installation, one at substantial completion of the roof work, and all others during different periods of installation. Notify the Contracting officer a minimum of 5 working days prior to each visit by the manufacturer's technical representative.

#### 3.7.2 Field Inspection Report

Document inspection results in a report prepared and signed by the manufacturer's technical representative for each visit. Submit the report to the Contracting Officer with the contractor's daily Quality Control report. The manufacturer's field inspection report must include a description of ongoing work observed and whether the inspected work was

satisfactory or unsatisfactory. The final report must include certification by the manufacturer's technical representative that the work was performed in accordance with the manufacturer's instructions and contains no deficiencies. Submit the final manufacturer's field inspection report to the Contracting Officer within 5 working days of the final visit.

### 3.8 COMPLETED WORK

Completed work must be plumb and true without oil canning, dents, ripples, abrasion, rust, staining, or other damage detrimental to the performance or aesthetics of the completed roof assembly.

### 3.9 INFORMATION CARD

For each roof, provide a typewritten card, laminated in plastic and framed for interior display or a photoengraved 0.8 mm thick 0.032 inch thick aluminum card for exterior display. Card to be 220 by 280 mm 8 1/2 by 11 inches minimum and contain the information listed on Form 1 at end of this Section. Install card near point of access to roof, or where indicated. Provide an electronic copy of the Information Card to the Contracting Officer's Representative.

### 3.10 SCHEDULE

Some metric measurements in this Section are based on mathematical conversion of English unit measurements, and not on metric measurement commonly agreed to by the manufacturers or other parties. The English and metric units for the measurements shown are as follows:

<u>PRODUCTS</u>	<u>ENGLISH UNITS</u>	<u>METRIC UNITS</u>
a. Steel sheets	0.023 inch	0.6 mm
	0.030 inch	0.8 mm
b. Gasket washers	3/8 inch	10 mm
	1/8 inch	3 mm
c. Screws	No. 14	4.75 mm
	No. 12	4 mm
d. Bolts	1/4 inch	6 mm
e. Studs	3/16 inch	5 mm
f. Fasteners	0.145 inch by 1/2 inch	4 mm by 13 mm
	One inch	25 mm
g. Rivets	1/8 inch	3 mm

3.11 FORM ONE

FORM 1 - PREFORMED STEEL STANDING SEAM ROOFING SYSTEM COMPONENTS

1. Contract Number:
2. Building Number & Location:
3. NAVFAC Specification Number:
4. Deck/Substrate Type:
5. Slopes of Deck/Roof Structure:
6. Insulation Type & Thickness:
7. Insulation Manufacturer:
8. Vapor Retarder: ( )Yes ( )No
9. Vapor Retarder Type:
10. Preformed Steel Standing Seam Roofing Description:
  - a. Manufacturer (Name, Address, & Phone No.):
  - b. Product Name:
  - c. Width:
  - d. Gage:
  - e. Base Metal:
  - f. Method of Attachment:
11. Repair of Color Coating:
  - a. Coating Manufacturer (Name, Address & Phone No.):
  - b. Product Name:
  - c. Surface Preparation:
  - d. Recoating Formula:
  - e. Application Method:
12. Statement of Compliance or Exception: \_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_
13. Date Roof Completed:
14. Warranty Period: From \_\_\_\_\_ To \_\_\_\_\_
15. Roofing Contractor (Name & Address):
16. Prime Contractor (Name & Address):

Contractor's Signature \_\_\_\_\_ Date:

Inspector's Signature \_\_\_\_\_ Date:

-- End of Section --